

RK-1300 Structural Acrylic Adhesive



Pasty | strong | fast-curing

The structural acrylic adhesive WEICON RK-1300 has high impact, peel and shear strength. The system consists of one adhesive and one activator, which are used in the “no mix” procedure. This makes processing easier by eliminating mixing procedures. The product is particularly suitable for bonding large surfaces of many different materials such as metals, ferrites and rigid plastics. WEICON RK-1300 can be used in mechanical and apparatus engineering, vehicle construction, tool and mould making, the building and furniture industry, and in many other industrial areas.

Characteristics

Base	methyl methacrylate	
Texture	pasty	
Colour	beige, opaque	

Processing

Processing procedure	No-Mix	
Processing temperature	+10°C to +40°C	
Curing temperature	mind. +18 °C	
Cure temperature	+18	
Density of the mixture	1,2 g/cm ³	
Gap bridging up to max.	0.4 mm	

Curing

Handling strength	(35 % strength)	6 min.
Working strength after	(50 % strength)	9 min.
Final strength	(100 % strength)	24 h

Mechanical properties after curing

Lap shear strength material thicken. 1,5mm DIN EN 1465	
Steel 1.0338 sandblasted	25 N/mm ²
Stainless steel V2A sandblasted	25 N/mm ²
Aluminium sandblasted	20 N/mm ²
PVC-rigid roughened	7 N/mm ²
CFRP	24 N/mm ²
ABS	6 N/mm ²
PC (polycarbonate)	10 N/mm ²
GFRP	16 N/mm ²
PMMA	9 N/mm ²
Polyamide 6.6	2 N/mm ²

Thermal parameters

Temperature resistance	-50 °C to +130 °C, briefly up to +180 °C
------------------------	--

Approvals / Guidelines

ISSA Code	75.629.52
IMPA Code	812991

Instructions for use

When using WEICON products, the physical, safety-related, toxicological and ecological data and regulations in our EC safety data sheets (www.weicon.com) must be observed.

Surface pre-treatment

Clean and dry bonding surfaces are essential for flawless adhesive bonding (e.g. cleaning and degreasing with WEICON Surface Cleaner). Higher strengths can be achieved by further pre-treatment of the surfaces, such as roughening by blasting or grinding. Some plastics, especially polyamides, PTFE, polyolefines etc., can only be bonded after special pre-treatment of the surfaces by e.g. fluorination, low-pressure plasma, corona, flame treatment, or similar.

Processing

Processing the RK Activator: Depending on the size of the bonding gap, the RK Activator is applied to one or both sides of the bonding surfaces (brush, spray, dip). For adhesive gaps up to max. 0.4 mm, a single-sided application is sufficient; for adhesive gaps up to max. 0.8 mm and/or rough, porous as well as passive surfaces (chrome, nickel, etc.), a double-sided application is required. For smooth plastic and metal surfaces approx. 30 g/m², for rough and porous surfaces up to 150 g/m² activator are required. The flash-off time is at least 5 minutes at room temperature (+20°C). A significant advantage over other adhesive systems is that the coated workpieces can be stored at room temperature (+20°C) for up to 30 days without the effectiveness decreasing.

Processing of the RK Adhesive: The adhesive is only applied on to side and usually to the surface not coated with activator. The bonding gap can be up to 0.80 mm (only with activator applied to both sides). Adhesive joints with a thickness of 0.15 mm to 0.25 mm generally have the highest tensile shear strength. For smooth plastic and metal surfaces approx. 180 g/m², for rough and porous surfaces up to 300 g/m² activator are required. Processing temperature: The processing should be done at room temperature (+20°C). Higher temperatures e.g.

Note
Alle in diesem Technischen Datenblatt enthaltenen Angaben und Empfehlungen stellen keine zugesicherten Eigenschaften dar. Sie beruhen auf unseren Forschungsergebnissen und Erfahrungen. Sie sind jedoch unverbindlich, da wir für die Einhaltung der Verarbeitungsbedingungen nicht verantwortlich sein können, da uns die speziellen Anwendungsverhältnisse beim Verwender nicht bekannt sind. Eine Gewährleistung kann nur für die stets gleichbleibende hohe Qualität unserer Erzeugnisse übernommen werden. Wir empfehlen, durch ausreichende Eigenversuche festzustellen, ob von dem angegebenen Produkt die von Ihnen gewünschten Eigenschaften erbracht werden. Ein Anspruch daraus ist ausgeschlossen. Für falschen oder zweckfremden Einsatz trägt der Verarbeiter die alleinige Verantwortung.

WEICON Middle East L.L.C.
United Arab Emirates
phone +971 4 880 25 05
info@weicon.ae

WEICON Czech Republic s.r.o.
Czech Republic
phone +42 (0) 417 533 013
info@weicon.cz

WEICON GmbH & Co. KG
(Headquarters) Germany
phone +49 (0) 251 9322 0
info@weicon.de

WEICON Romania SRL
Romania
phone +40 (0) 3 65 730 763
office@weicon.com

WEICON South East Asia Pte Ltd
Singapore
Phone (+65) 6710 7671
info@weicon.com.sg

WEICON Inc.
Canada
phone +1 877 620 8889
info@weicon.ca

WEICON Ibérica S.L.
Spain
phone +34 (0) 914 7997 34
info@weicon.es

WEICON Italia S.r.l.
Italy
phone +39 (0) 10 2924 871
info@weicon.it

WEICON SA (Pty) Ltd
South Africa
phone +27 (0) 21 709 0088
info@weicon.co.za

WEICON Kimya Sanayi Tic. Ltd. Şti.
Turkey
phone +90 (0) 212 465 33 65
info@weicon.com.tr

RK-1300 Structural Acrylic Adhesive

+40°C shorten the positioning and curing times by approx. 30%; low temperatures around +10°C increase the respective times by approx. 50%, until from +5°C almost no reaction takes place.

Storage

WEICON RK Construction Adhesives have a shelf life of at least 12 months at constant room temperature of approx. +20°C and dry storage, while at temperatures between +1°C and +7°C the shelf life can be extended up to 24 months. This applies to closed original containers that are not exposed to direct or indirect sunlight. If the storage temperature exceeds +40°C and the air humidity is high, the storage stability is reduced to 6 months.

Scope of delivery

RK1500 mass | Activator | Wooden spatula | Tip for RK1300/1500

Accessories

10010887 Processing Spatula, 1 PCE
 10022562 Processing Spatula, 1 PCE
 10032350 Primer Applicator, 1 PCE

Conversion table

(°C x 1.8) + 32 = °F	Nm x 8.851 = lb·in
mm/25.4 = inch	Nm x 0.738 = lb·ft
µm/25.4 = mil	Nm x 141.62 = oz·in
N x 0.225 = lb	mPa·s = cP
N/mm ² x 145 = psi	N/cm x 0.571 = lb/in
MPa x 145 = psi	kV/mm x 25.4 = V/mil

Available sizes

10000118 RK-1300 Structural Acrylic Adhesive, 60 g, beige, opaque
 10000126 RK-1300 Structural Acrylic Adhesive, 6 kg, beige, opaque
 10007508 RK-1300 Structural Acrylic Adhesive, 0,33 kg, beige, opaque
 10007378 RK-1300 Structural Acrylic Adhesive, 1 kg, beige, opaque

To the product detail page:



Note
 Alle in diesem Technischen Datenblatt enthaltenen Angaben und Empfehlungen stellen keine zugesicherten Eigenschaften dar. Sie beruhen auf unseren Forschungsergebnissen und Erfahrungen. Sie sind jedoch unverbindlich, da wir für die Einhaltung der Verarbeitungsbedingungen nicht verantwortlich sein können, da uns die speziellen Anwendungsverhältnisse beim Verwenden nicht bekannt sind. Eine Gewährleistung kann nur für die stets gleichbleibende hohe Qualität unserer Erzeugnisse übernommen werden. Wir empfehlen, durch ausreichende Eigenversuche festzustellen, ob von dem angegebenen Produkt die von Ihnen gewünschten Eigenschaften erbracht werden. Ein Anspruch daraus ist ausgeschlossen. Für falschen oder zweckfremden Einsatz trägt der Verarbeiter die alleinige Verantwortung.

WEICON Middle East L.L.C.
 United Arab Emirates
 phone +971 4 880 25 05
 info@weicon.ae

WEICON Czech Republic s.r.o.
 Czech Republic
 phone +42 (0) 417 533 013
 info@weicon.cz

WEICON GmbH & Co. KG
 (Headquarters) Germany
 phone +49 (0) 251 9322 0
 info@weicon.de

WEICON Romania SRL
 Romania
 phone +40 (0) 3 65 730 763
 office@weicon.com

WEICON South East Asia Pte Ltd
 Singapore
 Phone (+65) 6710 7671
 info@weicon.com.sg

WEICON Inc.
 Canada
 phone +1 877 620 8889
 info@weicon.ca

WEICON Ibérica S.L.
 Spain
 phone +34 (0) 914 7997 34
 info@weicon.es

WEICON Italia S.r.l.
 Italy
 phone +39 (0) 010 2924 871
 info@weicon.it

WEICON SA (Pty) Ltd
 South Africa
 phone +27 (0) 21 709 0088
 info@weicon.co.za

WEICON Kimya Sanayi Tic. Ltd. Şti.
 Turkey
 phone +90 (0) 212 465 33 65
 info@weicon.com.tr