WEICON

WEICONLOCK® **Anaerobic Adhesives and Sealants**

WEICONLOCK® AN 305-86 Pipe Sealing



Pipe sealing | extra strong

- · higher viscosity
- · high strength
- · hard to disassemble

Technical Data

Colour		red
Fluorescent		no
For thread connections up to		M 56 R 2"
Viscosity		6.000 - 7.000 nt mPa·s
Gap bridging up to max.		0,3 mm
Breakaway torque		15 - 30 Nm
Prevail torque		25 - 45 Nm
Shear strength Nmm	n² (DIN 54452)	10 - 20 N/mm²
Handling strength	at room temperature	60 - 90 min.
Final strength	(100 % strength)	12-24 h
Temperature resistance		-60°C to +150°C
Compressive strength (free cutting steel / grub screw = 8.8)		
M_3x6	max.	1500 bar
M_4x6	max.	1500 bar
M_5x8	max.	1300 bar
M_6x10	max.	700 bar
M_8x12	max.	600 bar
M_10x16	max.	500 bar
Approvals / Guideli	nes	
MIL-Spec	comply with	MIL-S-46163 A Type I Grade L

Surface pre-treatment

Clean surfaces to be sealed.

Processing

WEICONLOCK is applied evenly straight from the Pen with the help of the dosing tip; avoid direct contact between dosing tip/metal. Apply WEICONLOCK to the thread in circles. Screw the pipe thread together and tighten it to the desired alignment. When used as flange sealing, apply a continuous bead to one flange side, then assemble parts quickly and screw tight. Do not pour any WEICONLOCK back into the bottle that has already come into contact with metal. Even extremely small metal particles cause the adhesive to cure inside the bottle. Therefore, in serial production, the use of dosing devices is recommended.

Storage

Shelf life: at least 24 months at room temperature (+20°C).

Instructions for use

When using WEICON products, the physical, safety-related, toxicological and ecological data and regulations in our EC safety data sheets (www.weicon.com) must be observed.

Accessories

10021433 Activator F, 200 ml, green 10001256 Dosing Tip, 1 PCE

Available sizes

10017879

WEICONLOCK® AN 305-86 Pipe Sealing, 20 10019907 WEICONLOCK® AN 305-86 Pipe Sealing, 200 10020013 WEICONLOCK® AN 305-86 Pipe Sealing, 50

ml, red



The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the requested properties are recommended. A claim cannot be derived from them.

Italy phone +39 (0) 010 2924 871

WEICON Romania SRL phone +40 (0) 3 65 730 763

WEICON SA (Pty) Ltd South Africa phone +27 (0) 21 709 0088 info@weicon.co.za

WEICON South East Asia Pte Ltd ne (+65) 6710 7671

WEICON Kimya Sanayi Tic. Ltd. Sti. Turkey phone +90 (0) 212 465 33 65