

WEICONLOCK® AN 306-01 Retaining Cylindrical Assemblies



Retaining cylindrical assemblies for bearings | shafts and bushings

- low viscosity
- high strength
- hard to disassemble

Technical Data

Colour	green
Fluorescent	yes
For thread connections up to	M 12
Viscosity	125 nt mPa·s
Gap bridging up to max.	0,1 mm
Breakaway torque	25 - 30 Nm
Prevail torque	50 - 60 Nm
Shear strength Nmm ² (DIN 54452)	17-22 N/mm ²
Handling strength	10 - 20 min.
Final strength (100 % strength)	2-4 h
Temperature resistance	-60°C to +150°C
Compressive strength (free cutting steel / grub screw = 8.8)	
M_3x6 max.	1500 bar
M4x6 max.	1500 bar
M5x8 max.	1500 bar
M6x10 max.	900 bar
M8x12 max.	800 bar
M10x16 max.	500 bar

Approvals / Guidelines

ISSA Code	75.628.15/16/17
IMPA Code	815216/17/18

Anaerobic Adhesives and Sealants

Surface pre-treatment

To achieve optimum results, the mounting parts should be degreased and cleaned, e.g. with WEICON Surface (roughen the surfaces, if required). WEICONLOCK can also be used on uncleaned surfaces, e.g. screws as delivered. However, the cleaner the surface, the better the results achieved.

Processing

WEICONLOCK is applied evenly straight from the Pen with the help of the dosing tip; avoid direct contact between dosing tip/metal. In the case of pressed joints and larger parts to be joined, both surfaces should always be wetted thinly and evenly. Join parts swiftly. For sliding seats, twist parts against each other when joining for optimum spreading of the adhesive. Bonded parts should not be moved until handling strength is reached. Do not pour any WEICONLOCK back into the bottle that has already come into contact with metal. Even extremely small metal particles cause the adhesive to cure inside the bottle. Therefore, in serial production, the use of dosing devices is recommended.

Storage

WEICONLOCK has a shelf life of at least 24 months, when stored at room temperature in closed original container. Protect from heat sources and direct sunlight. The air contained in the Pen keeps WEICONLOCK liquid.

Instructions for use

When using WEICON products, the physical, safety-related, toxicological and ecological data and regulations in our EC safety data sheets (www.weicon.com) must be observed.

Accessories

- 10021433 Activator F, 200 ml, green
- 10001256 Dosing Tip, 1 PCE

Available sizes

10000559	WEICONLOCK® AN 306-01	Retaining Cylindrical
10017880	WEICONLOCK® AN 306-01	Retaining Cylindrical Assemblies, 50 ml, green
10020017	WEICONLOCK® AN 306-01	Retaining Cylindrical Assemblies, 50 ml, green
10020045	WEICONLOCK® AN 306-01	Retaining Cylindrical Assemblies, 200 ml, green
		Assemblies, 20 ml, green

Note

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

WEICONLOCK® AN 306-01 Retaining Cylindrical Assemblies

WEICONLOCK® Anaerobic Adhesives and Sealants

To the product detail
page:



Note

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

WEICON Middle East L.L.C.
United Arab Emirates
phone +971 4 880 25 05
info@weicon.ae

WEICON Czech Republic s.r.o.
Czech Republic
phone +42 (0) 417 533 013
info@weicon.cz

WEICON GmbH & Co. KG
(Headquarters) Germany
phone +49 (0) 251 9322 0
info@weicon.de

WEICON Romania SRL
Romania
phone +40 (0) 3 65 730 763
office@weicon.com

WEICON South East Asia Pte Ltd
Singapore
Phone (+65) 6710 7671
info@weicon.com.sg

WEICON Inc.
Canada
phone +1 877 620 8889
info@weicon.ca

WEICON Ibérica S.L.
Spain
phone +34 (0) 914 7997 34
info@weicon.es

WEICON Italia S.r.l.
Italy
phone +39 (0) 010 2924 871
info@weicon.it

WEICON SA (Pty) Ltd
South Africa
phone +27 (0) 21 709 0088
info@weicon.co.za

WEICON Kimya Sanayi Tic. Ltd. Şti.
Turkey
phone +90 (0) 212 465 33 65
info@weicon.com.tr