WEICONLOCK[®] AN 306-20 Retaining Cylindrical Assemblies



Retaining cylindrical assemblies | high-temperatureresistant | drinking water and DVGW approval | BAM

- · higher viscosity
- high strength
- · hard to disassemble

Technical Data

Colour		green
Fluorescent		yes
For thread connections up to		M 56 R 2"
Viscosity		3.000 - 6.000 nt mPa·s
Gap bridging up to max.		0,2 mm
Breakaway torque		28 - 36 Nm
Prevail torque		40 - 55 Nm
Shear strength Nmm ² (DIN 54	452)	15 - 25 N/mm²
Handling strength		20 - 40 min.
Final strength	(100 % strength)	24 h
Temperature resistance		-60°C to +200°C
Compressive strength (free cu	utting steel / grub screw = 8.8)	
M_3x6	max.	1500 bar
M4x6	max.	1500 bar
M5x8	max.	1500 bar
M6x10	max.	1300 bar
M8x12	max.	1000 bar
M10x16	max.	500 bar
Approvals / Guidelines		

Hygiene Institute	UBA KTW-BWGL
IMPA Code	450842

WEICONLOCK® Anaerobic Adhesives and Sealants

Surface pre-treatment

To achieve optimum results, the mounting parts should be degreased and cleaned, e.g. with WEICON Surface (roughen the surfaces, if required). WEICONLOCK can also be used on uncleaned surfaces, e.g. screws as delivered. However, the cleaner the surface, the better the results achieved.

Processing

WEICONLOCK is applied evenly straight from the Pen with the help of the dosing tip; avoid direct contact between dosing tip/metal. In the case of pressed joints and larger parts to be joined, both surfaces should always be wetted thinly and evenly. Join parts swiftly. For sliding seats, twist parts against each other when joining for optimum spreading of the adhesive. Bonded parts should not be moved until handling strength is reached. Do not pour any WEICONLOCK back into the bottle that has already come into contact with metal. Even extremely small metal particles cause the adhesive to cure inside the bottle. Therefore, in serial production, the use of dosing devices is recommended.

Storage

WEICONLOCK has a shelf life of at least 24 months, when stored at room temperature in closed original container. Protect from heat sources and direct sunlight. The air contained in the Pen keeps WEICONLOCK liquid.

Instructions for use

When using WEICON products, the physical, safety-related, toxicological and ecological data and regulations in our EC safety data sheets (www.weicon.com) must be observed.

Accessories

10021433	Activator F, 200 ml, green
10001256	Dosing Tip, 1 PCE

Available sizes

10017330	WEICONLOCK [®] Cylindrical	AN	306-20	Retaining
10000571	Assemblies, 20 ml, WEICONLOCK [®] Cylindrical	, green AN	306-20	Retaining
10017885	Assemblies, 50 ml, WEICONLOCK [®] Cylindrical	, green AN	306-20	Retaining
10020023	Assemblies, 50 ml, WEICONLOCK [®] Cylindrical	, green AN	306-20	Retaining

Assemblies, 200 ml, green

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarante the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

WEICON Middle East L.L.C. United Arab Emirates phone +971 4 880 25 05 info@weicon.ae

WEICON Inc. Canada phone +1 877 620 8889 info@weicon.ca WEICON Czech Republic s.r.o. Czech Republic phone +42 (0) 417 533 013 info@weicon.cz

WEICON Ibérica S.L. Spain phone +34 (0) 914 7997 34 info@weicon.es WEICON GmbH & Co. KG (Headquaters) Germany phone +49 (0) 251 9322 0 info@weicon.de

WEICON Italia S.r.L. Italy phone +39 (0) 010 2924 871 info@weicon.it WEICON Romania SRL Romania phone +40 (0) 3 65 730 763 office@weicon.com

WEICON SA (Pty) Ltd South Africa phone +27 (0) 21 709 0088 info@weicon.co.za WEICON South East Asia Pte Ltd Singapore Phone (+65) 6710 7671 info@weicon.com.sg

WEICON Kimya Sanayi Tic. Ltd. Şti. Turkey phone +90 (0) 212 465 33 65 info@weicon.com.tr Technical data sheet - Page: 2/2 Date of issue:20.02.2024

WEICONLOCK[®] AN **306-20 Retaining Cylindrical Assemblies**

WEICON®

WEICONLOCK[®] Anaerobic Adhesives and Sealants

To the product detail page:



Note The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

WEICON Middle East L.L.C. United Arab Emirates phone +971 4 880 25 05 info@weicon.ae

WEICON Inc. Canada phone +1 877 620 8889 info@weicon.ca WEICON Czech Republic s.r.o. Czech Republic phone +42 (0) 417 533 013 info@weicon.cz

WEICON Ibérica S.L. Spain phone +34 (0) 914 7997 34 info@weicon.es WEICON GmbH & Co. KG (Headquaters) Germany phone +49 (0) 251 9322 0 info@weicon.de

WEICON Italia S.r.L. Italy phone +39 (0) 010 2924 871 info@weicon.it WEICON Romania SRL Romania phone +40 (0) 3 65 730 763 office@weicon.com

WEICON SA (Pty) Ltd South Africa phone +27 (0) 21 709 0088 info@weicon.co.za

WEICON South East Asia Pte Ltd Singapore Phone (+65) 6710 7671 info@weicon.com.sg

WEICON Kimya Sanayi Tic. Ltd. Şti. Turkey phone +90 (0) 212 465 33 65 info@weicon.com.tr